

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

WE CLAIM:

1. A unitary film structure of a polymeric resin comprising a base film layer having generally parallel upper and lower major surfaces having projections being
5 arranged in rows with at least 25 spaced projections per centimeter in a row projecting from at least the upper surface of said base.

2. The unitary structured film of claim 1 wherein the projections are hook
10 members which have head portions that extend in a direction transverse to the direction of rows of the hook members.

3. A unitary hook fastener according to claim 2 having at least 30 spaced hook
members per centimeter in a row.

15 4. A unitary hook fastener according to claim 2 wherein said polymeric material is a thermoplastic resin and the hook head has rounded corners.

5. A unitary hook fastener according to claim 2 having at least 50 spaced hook
20 members per centimeter in a row.

6. A unitary hook fastener according to claim 5 wherein said polymeric
material comprises polyethylene, polypropylene, polypropylene-polyethylene copolymers or blends thereof.

25 7. The unitary hook fastener according to claim 2 wherein at least the hook head portion has a molecular orientation of less than 10 percent.

8. The unitary hook fastener according to claim 7 wherein the hook member
30 base portion adjacent the base has a molecular orientation of at least 10 percent.

9. The unitary hook fastener according to claim 7 wherein the base film layer
is substantially unoriented.

10. A method of forming a strip with upstanding projections comprising the steps of forming a thermoplastic resin into a base portion and one or more ridges extending from at least one side of the base portion, inducing orientation into at least the ridges, cutting the ridge portions into a plurality of cut portions, and subsequently heat
5 treating at least a portion of the cut portions of the ridges at a temperature and time sufficient to reduce the thickness of the cut portions to form discrete projections.

11. The method of claim 10 wherein the orientation is induced into the ridges
10 by extruding the thermoplastic resin in a machine direction through a die plate having a continuous base portion cavity and one or more ridge cavities, the extrusion rate being sufficient to induce melt flow molecular orientation in the polymer flowing through at least the ridge cavities.

12. The method of claim 10 wherein the molecular orientation is induced by
15 stretch orientation of at least the ridge portions.

13. The method of forming the strip of claim 10 wherein the projections are
20 hook form projections having a stem portion and a head portion, and the strip is a film strip.

14. A method for forming strip of claim 10 wherein the projections are heated
at a temperature and time sufficient to shrink at least a portion of the projections by from 5
to 90 percent.

15. A method for forming the film strip of claim 12 wherein the hook portions
25 are formed by extruding continuous ridges having a profile of the hook element, cutting the ridges and subsequently heating the cut portion of the ridges to separate the individual cut ridges into discrete hook portions, separated at least 10 μm .

16. A method for forming the film strip of claim 15 wherein at least a portion
30 of the hook head portions are shrunk by at least 30 percent.

17. A method for forming the film strip of claim 15 wherein portions of the head and stem portions are shrunk at least in part by 30 percent.